



Product Data Sheet

PRODUCT DESCRIPTION

7470-002 is a single component, aliphatic polyurethane coating designed for use as a weather protective topcoat for vehicular traffic bearing waterproofing systems.

7470-002 must be mixed thoroughly before use. Allow 72 hours cure time at 77°F, 50% RH before allowing vehicular traffic on coating.

PRODUCT NUMBERS AND COLORS

Standard color is: 7470-002 Gray

CURED RESIN PERFORMANCE

Description	Test Method	Results
Tensile Strength	ASTM D412	2,500 psi
Elongation	ASTM D412	250%
Permanent Set	ASTM D412	<20%
Tear Resistance	ASTM D1004	400 pli
Water Resistance	ASTM D471	1%, 7 Days
MVT @ 20 mils	ASTM E96	2.5 English Perm
Taber Abrasion	ASTM D4060	10 mg/cs17
Shore A	ASTM D2240	88 - 92
Adhesion to: 70714/70715, 7760/7761, 7780/7781, 7795/7796, 70410, 7430, FC7500/FC7960, FC7510/FC7961, FC7520/FC7962, FC7530/FC7963	ASTM D4541	>400 psi

The above tested results are typical values. Individual lots may vary up to 10% from the typical value.

PRODUCT DATA

Description	Test Method	Results
Weight/Gal	ASTM D1475	8.95 lbs/gal
Weight Solids	ASTM C1250	81.8% @ 12 hrs
Volume Solids	Calculated	77.7%
VOC	EPA Method 24	195 g/L
Viscosity	ASTM D2196	84 KU
Flash Point	By Comparison	110°F
Cure Time, 77°F, 50% RH		72 hrs for Vehicular Traffic

The above tested results are typical values. Individual lots may vary up to 10% from the typical value.

HEALTH AND SAFETY

Read the Material Safety Data Sheet (MSDS) and container labels for detailed health and safety information. This product is intended for industrial use by properly trained professional applicators only.

The information, data and suggestions contained herein are believed to be reliable, based upon our knowledge and experience; however, it is expressly declared that Seller does not guarantee the result to be obtained in Buyer's process. **SELLER HEREBY EXPRESSLY DISCLAIMS ANY IMPLIED WARRANTY OF MERCHANTABILITY FOR FITNESS FOR A PARTICULAR PURPOSE AND/OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED** as to any and all products and/or suggestions described herein, whether such products are used alone or in combination with other materials. Buyer must make its own determination of the suitability of any product for its use, and the completeness of any information contained herein. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. Applicator is an independent contractor of, and should under no circumstances be viewed as an employee or agent of, the NEOGARD® Division of JONES-BLAIR®. 03112008/7470-002PD.indd

NEOGARD®
Div. of JONES-BLAIR®

2728 Empire Central - P.O. Box 35286 - Dallas, Texas 75235 - Toll Free (800) 321-6588 - Fax (214) 357-7532 - www.neogard.com